

# SOUTH PACIFIC REDWOOD



## WHAT IS SOUTH PACIFIC REDWOOD?


South Pacific Redwood, also known as Manilkara, is a lustrous reddish-brown hardwood that is known for its strength and durability. Coming primarily from South East Asia, South Pacific Redwood is part of a wide genus that can be found around the world in various locations. South Pacific Redwood is an excellent cost-effective alternative to Ipe with its similar hardness and density.

## THE BETTER INVESTMENT

Those who are looking for a wood that is rich in color and built to last, look no further than South Pacific Redwood. With a 25+ year warranty and a service life expectancy of 50+ years, South Pacific Redwood is suitable for all outdoor applications. This particular species will readily accept most oil-based stains and finishes.

## SUSTAINABLE AND CERTIFIED

Our stock of South Pacific Redwood is Lacey Act approved and comes with a V-Legal license which is at the heart of Indonesia's timber legality verification system.



Nova USA Wood Products  
3821 24th Ave  
Forest Grove, OR 97116  
(503) 419-6407

[www.novausawood.com/  
south-pacific-redwood-decking](http://www.novausawood.com/south-pacific-redwood-decking)



## TECHNICAL SPECIFICATIONS

Janka Hardness: 3,130 lbf

Strength (MOR): 27,870 lbf/in<sup>2</sup>

Stiffness (MOE): 3,344,000 lbf/in<sup>2</sup>

Density (KG/m<sup>3</sup>): 1000KG/m<sup>3</sup>

Color: Medium to dark reddish brown.

Tangential Shrinkage: 9.4%

Radial Shrinkage: 6.7%

Family: Manilkara

Geographic Area: Indonesia, Malaysia

Texture: Fine uniform texture.

Grain: Straight to interlocked or wavy.

Luster: Uniform luster low to medium.

Durability Rating: Rated as very durable.

Drying Characteristics: All of Nova's Manilkara/  
South Pacific Redwood is kiln dried.

Working Characteristics: The wood is moderately  
easy to work despite its high density.



@NovaUSAWood

