

| | | |
|------|--------------------|---------------------------------------|
| 2X4 | 12' 16' 20' | <i>Janka Hardness: 470</i> |
| 2X6 | 12' 16' 20' | <i>Strength (MOR): 8,000 psi</i> |
| 2X8 | 12' 16' 20' | <i>Stiffness (MOE): 1,040,000 psi</i> |
| 2X10 | 16' 20' | <i>Density (KG/m3): 385</i> |
| 2X12 | 16' 20' | <i>Photosensitivity: Moderate</i> |
| 3X6 | 12' 16' | <i>Tangential Shrinkage: 5.2%</i> |
| 3X8 | 12' 16' | <i>Radial Shrinkage: 3.3%</i> |
| 3X10 | 16' | <i>Family: Cupressaceae</i> |
| 3X12 | 16' | <i>Height: 65' to 100'</i> |
| 4X4 | 12' 16' | <i>Diameter: 2' to 5'</i> |
| 4X6 | 8' 10' 12' 16' | <i>Weight: 24 lbs per cubic foot</i> |
| 4X8 | 16' | |
| 4X10 | 12' 16' 20' | |
| 4X12 | 12' 16' 20' | |
| 6X6 | 8' 10' 12' 16' 20' | |
| 8X8 | 8' 10' 12' 16' 20' | |

Oversized timbers and long lengths are available for special order.