

3X6	12' 16' 20'	<i>Janka Hardness: 660</i>
3X8	12' 16' 20'	<i>Strength (MOR): 12,400 psi</i>
3X10	12' 16' 20'	<i>Stiffness (MOE): 1,950,000 psi</i>
3X12	12' 16' 20'	
4X4	8' 10' 12' 14' 16' 20'	<i>Density (KG/m3): 530</i>
4X6	12' 16' 20'	<i>Photosensitivity: Moderate</i>
4X8	12' 16' 20'	<i>Tangential Shrinkage: 7.9%</i>
4X10	12' 16' 20'	
4X12	12' 16' 20'	<i>Radial Shrinkage: 4.2%</i>
6X6	8' 10' 12' 14' 16' 20'	<i>Family: Pinaceae</i>
6X8	12' 16' 20'	<i>Height: 150' to 200'</i>
6X10	12' 16' 20'	
6X12	12' 16' 20'	<i>Diameter: 2' to 6'</i>
8X8	8' 10' 12' 14' 16' 20'	<i>Weight: 32 lbs per cubic foot</i>
8X10	12' 16' 20'	
8X12	12' 16' 20'	
10X10	8' 10' 12' 14' 16' 20'	
10X12	12' 16' 20'	
12X12	8' 10' 12' 14' 16' 20'	

Oversized timbers and long lengths are available for special order.